

PAB Materials Test System

Date of Receipt	6/7/2013 eLog entry # 3626
Sample Name/Description	Polycarbonate Channel
Sample	
Picture Location:	data base
Weight:	1.9 g
Dimensions/Area:	50 x 24 x 1 mm
Source:	Matt Toups
Preparation:	cleaned with air only
Submerging in LAr or LH2	x
Time in the airlock(hrs)	
Purge:	25 hours
Vacuum:	
Liquid Test	
Start Time/Date, End Time/Date :	5/9/2013 8:30 am, 5/10/2013 4:45 pm
PrM run # :	17350
Condenser state:	on
Filter state:	off
O2 reading:	x
H2O reading:	5 ppb
Temperature:	95 K
Lifetime:	5 ms
Liquid Level	24.5 inches
VaporTest	
Start Time/Date, End Time/Date :	5/13/2013 8:55 am, 5/15/2013 3:08 pm
PrM run # :	17444
Condenser state:	on
Filter state/settings:	off
O2 reading:	x
H2O reading:	8 ppb
Temperature:	216 K
Lifetime:	3.5 -4 ms
Liquid Level	23.5 inches
Results/comments	