

## **PAB Materials Test System**

<b>Date of Receipt</b>	8/26/2013 eLog entry # 4241
<b>Sample Name/Description</b>	Silicone rubber ring (small red ring) will be used for the UV laser feedthrough in MicroBooNE
<b>Sample</b>	
<b>Composition:</b>	Silicone rubber is an inorganic synthetic elastomer made from a crosslinked silicon-based polymer reinforced with filler
<b>Picture Location:</b>	data base
<b>Weight:</b>	1 g
<b>Dimensions/Area:</b>	ring -ID 30 mm, OD 36 mm,
<b>Source:</b>	Thomas Strauss
<b>Preparation:</b>	cleaned with cloth
<b>Submerging in LAr or LH2</b>	x
<b>Time in the airlock(hrs)</b>	
<b>Purge:</b>	for 23 hours from the bottle, 2 hour from Luke
<b>Vacuum:</b>	
<b>Room Test</b>	
<b>Start Time/Date, End Time/Date :</b>	8/21/13 2:10 pm, 8/26/2013 10:00 am
<b>PrM run # :</b>	18563
<b>Condenser state:</b>	on
<b>Filter state:</b>	off
<b>O2 reading:</b>	x
<b>H2O reading:</b>	increased to 32 ppb in 2 hours, then decreased and sabilized at 10-15 ppb
<b>Liquid level</b>	24.2 to 22.5 inches (approximately 170 kg of liquid argon in Luke)
<b>Lifetime:</b>	slowly decreased from >10 ms to 8-10 ms
<b>Results/comments</b>	