


SS Scrubber Pads Test 12/17/2015 – 1/4/2016

<i>PAB Materials Test System</i>	
Date of Receipt	1/12/2016
Sample Name/Description	4 SS scrubber pads
Sample	
Composition:	SS
Picture Location:	data base
Weight:	192.3 g
Dimensions/Area:	x
Source:	Stephen Pordes
Preparation:	x
Submerging in LAr or LH2	x
Time in the airlock(hrs)	
Vacuum:	30 min
Purge	24 hours with gas Argon from Luke
Liquid Test	
Start Time/Date, End Time/Date :	12/17/2015 3:08 PM , 12/21/2015 8:25 AM
PrM run # :	26313
Condenser state:	on
Filter state/settings:	off
H2O reading:	3 ppb
Temperature:	95 K
Liquid Level	22.1 - 21 inches
Lifetime:	6.5 ms
VaporTest	
Start Time/Date, End Time/Date :	12/21/2015 11:18 AM, 12/23/2015 9:20 AM
PrM run # :	26369
Condenser state:	on
Filter state/settings:	off
H2O reading:	3 ppb
Temperature:	217 - 220 K
Liquid Level	21 inches
Lifetime:	6 ms
Room Temperature Test	
Start Time/Date, End Time/Date :	12/23/2015 3:00 PM, 1/4/2016 11:30 AM
PrM run # :	264001
Condenser state:	on
Filter state/settings:	off
H2O reading:	12 ppb
Temperature:	room
Liquid Level	20.5-18 inches
Lifetime:	2-3 ms



1. Liquid test
2. Vapor Test
3. Room Temp.



Lifetime – green pen

Impurities – brown pen

Liquid level – yellow pen

Water – black pen

Temperature – magenta pen

