

PAB Materials Test System	
Date of Receipt	6/3/10 , logbook # 1283
Sample Name/Description	Teflon Tubing
Sample	
Composition:	Teflon
Picture Location:	Data Base
Weight:	11 g
Dimensions/Area:	length=1.66 m, OD=3.5 mm
Source:	Hans Jostlein
Preparation:	Cleaned with alcohol
Submerging in LAr	no
Zero Test	x
Time in the airlock(hrs)	total 18 h
Purge:	17 h from Luke
Vacuum:	1 h
Room Temperature	
Start Time/Date, End Time/Date :	5/27/10 9:10 am, 5/28/10 8:10 am
PrM run # :	8756
Condenser state:	on
Filter state:	off
O2 reading:	increased by 0.3 ppb
H2O reading:	9-13 ppb
Temperature:	room
Lifetime:	4-5 ms
Vapor Test	x
Liquid Test	x
Results & Comments	Teflon Tubing is save to use in LAPD